



Trowelite RS

Mortar retarder admixture for ready-to-use application

Description

Trowelite RS is formulated from selected polymers specially designed to work as a mortar retarder admixture that extends the workability retention for long time up to 72 hours. However, when the mortar is placed between absorbent masonry units or spread on the surface as in the plastering application, setting is accelerated and the mortar sets normally.

Applications

Trowelite RS is recommended for sand cement mortars to extend workability retention up to 72 hours, this property facilitate the provision of mortar to building sites by readymix suppliers.

Advantages

- ▲ Extending mortar workability retention up to 72 hours.
- ▲ Strength increase through water reduction.
- ▲ Quality assured control of mix proportions through the readymix supply.
- ▲ Eliminates the need for mixers and storage of materials on site.
- ▲ Compatible with most types of cement.
- ▲ Increased workability.
- ▲ Chloride free.

Compatibility

Trowelite RS can be used with most types of DCP admixtures. Contact DCP technical department for further details.

Standards

Trowelite RS complies with EN 934-3, T.3, as long term retarding admixture for masonry mortar.

Method of Use

Trowelite RS should be added to mortar with the mixing water to achieve optimum performance. An automatic dispenser should be used to dispense the correct quantity of Trowelite RS to the mortar mix.

Technical Properties @ 25°C:

| | |
|------------------------------|-------------|
| Colour: | Brown |
| Freezing point: | -5°C |
| Specific gravity: | 1.20 ± 0.02 |
| Chloride content: BS 5075 | Nil |

Dosage

The guidance dosage of Trowelite RS is 0.2% - 1.2% of cement weight.

When lime is used in the mortar, Trowelite RS should be dosed on the total amount at lime and cement in the mix.

Based on trials experience you can keep the mortar workable for more than 6 - 8 hours when you use Trowelite RS at 0.2% dosage and for more than 3 days when using dosage of 1.2%. However representative trials at laboratory should be conducted to determine the optimum dosage of Trowelite RS to meet the performance requirements by using the materials and conditions in actual use.

Cleaning

Trowelite RS can be washed with fresh cold water.

Packaging

Trowelite RS is available in 210 litre drums and 1000 litre bulks supply.

Storage

Trowelite RS has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C to 40°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Don Construction Products - Jordan

Showroom (1):

Khalda Street, Al-Darraas Building # 276

Showroom (2):

AlHurriyah Street, Near Alhamaidah Circle,
Building # 66

Trowelite RS

Cautions

Health and Safety

Trowelite RS is not classified as hazardous material. Trowelite RS should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data Sheet.

Fire

Trowelite RS is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Don Construction Products - Jordan

Showroom (1):


Khalda Street, Al-Darraas Building # 276

Showroom (2):


AlHurriyah Street, Near Alhamaidah Circle,
Building # 66

Note:

We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, DCP cannot accept any liability either directly or indirectly arising from the use of DCP products, whether or not in accordance with any advice, specification, recommendation or information given by us.

 expertise

 quality

 full range

www.dcp-int.com